



www.daltek.cz
+420 721 932 393
daltek@daltek.cz

SÍDLO FIRMY - PRAHA
Sokolská č.p.1792/52
120 00 Praha Nové město

Duplexní ocel						Chemické složení					
EURONORM/DIN	W.Nr.	AISI	UNS	ČSN	Jiné	C (%)	Cr (%)	Ni (%)	Mo (%)	N (%)	ostatní prvky
X2CrNiN23-4	1.4362		S32304		URANUS 35N / SAF2304	max 0,030	23,0	4,5		N	
X2CrNiMoN25-7-4	1.4410	F53	S32750		SAF2507	max 0,030	25,00	7,0	4,00	0,30	
X3CrNiMoN27-5-2	1.4460	329	S32900		SS 44 / 10RE51	max 0,05	25,0-28,0	4,5-6,5	1,30-2,00	0,05-0,20	
X2CrNiMoN22-5-3	1.4462	F51	S31803	17381	URANUS 45 N / SAF2205	max 0,030	22,0	5,0	3,20	0,18	
X2CrNiMoN22-5-3	1.4462	F60	S32205		URANUS 45 N / SAF2205	max 0,030	22,0	5,5	3,00	0,18	
X2CrNiMoCuWN25-7-4	1.4501	F55	S32760		ZERON 100	max 0,030	24,0-26,0	6,0-8,0	3,00-4,00	0,20-0,30	Cu, W
X2CrNiMoCuN25-6-3	1.4507	F61	S32550		URANUS 52 N	max 0,030	24,0-26,0	5,5-7,5	2,70-4,00	0,15-0,30	Cu